



# NORTHERN INDIA TEXTILE RESEARCH ASSOCIATION

(Linked to Ministry of Textiles, Government of India)

Sector-23, Rajnagar, Ghaziabad-201 002, India, Fax : 0120-2783596, E-mail: mail@nitratextile.org  
 Phone : 0120-2786434/451, 2783334/586/592/638/090/094/095, Website: www.nitratextile.org

## TEST REPORT

(  Chemical  ECO  Environmental  Physical  Polymer & Technical Textiles  COE )

M/s Central Public Works Department Subdivision -3, Parliament House Civil Works Division, Parliament House, New Delhi	R-03A
	Report No.: 1246/17-CQE
	Customer's Reference : Letter No-9(8)/AE-III/P.H.C.W.D/2017-18/294(2) dt. 14.09.2017
	Dispatch Ref : NITRA/CQE/17-18/ 5679 Date : 09.10.2017

Sample Description : One sample described by Customer as "Fire Retardant Fabric, Dark Brown Colour, W.O. No. : 12/EE/PHCWD/2017-18" Sample submitted by M/s Mags Noval

Date of sample receiving : 03.10.2017

Date of results reporting : 09.10.2017

Sl. No	Test Parameter	Test Method	Test Results ( SC : 2583 )					
			Warp Direction			Weft Direction		
			Specimen No.			Specimen No.		
1.	Limited flame spread - Single Layer ( Pretreatment -None) - Any part of hole reached the top edge or either vertical edge - Any part of the lowest boundary of any flame reached the top edge or either vertical edge - Separation of flaming debris droplet	BS 5867 Part 2 Type B - 2008	1	2	3	1	2	3
			No	No	No	No	No	No
			No	No	No	No	No	No
			No	No	No	No	No	No


Any Observation/ Comments : Sample meets the requirement of BS 5867: 2008, Pt. 2, Type B

Auhorised Signatory

Head of Division /Officer In-charge

Page 1 of 1

End of Report



**Note:**

- The results are for technical information of client only, not for advertisement, promotion, publicity and litigation.
- The results refer to the applicable parameters only.
- Test results are based on samples as supplied by the client.
- The samples will be preserved for 60 days from the date of dispatch of report, subject to the condition that they are stable.
- Any discrepancy in the test report shall be notified to the lab within ten days of dispatch of report. Otherwise it is presumed that the report has met client's requirement.

No.: 0068071